

Primid® XL-552

Crosslinker for exterior durable powder coatings

Characteristics

- curing from 165°C
- proven exterior durability in Florida
- excellent powder coating storage stability
- enhanced charging properties
- no hazard labelling required

Description

Primid® XL-552 is a hydroxyalkylamide crosslinker for the formulation of exterior durable powder coatings. It can be used in combination with carboxyl-terminated polyesters. The constant and high reactivity of Primid® XL-552 combined with a favourable toxicological profile makes this crosslinker the industry standard for exterior durable powder coatings.

Product Specifications

Colour Gardner (50% in water)		max. 1.0
Melting point (Tottoli)	[°C]	120 - 124
Water content (Karl Fischer)	[%]	max. 1.0
Hydroxyl number (EMS method)	[mgKOH/g]	620 - 700

Typical Properties

Appearance	white granular solid
Bulk-Density	[g/cm ³] approx. 0.7
Shelf life	1 year from the date of delivery
Storage in a dry place at temperatures between 0°C and 40°C	

PRIMID®
EMS

Powder coating formulation

Carboxylated polyester resins with an acid value from about 20 to 80 are preferred for curing with Primid® XL-552. A large number of suitable resins for a wide range of powder coating applications are available from your resin supplier.

Starting formulation, white:

	by weight
Polyester resin, adic value 33	560.5
Primid® XL-552	29.5
Flow control agent ¹	8.0
Benzoin ²	2.0
Titanium dioxide ³	400.0
Total	1000.0

¹ Resiflow PV 88, Worlée Chemie GmbH or BYK-368 P, BYK-Chemie GmbH

² DSM

³ Kronos 2160, Kronos Titan GmbH

Curing cycles of the starting formulation

20 minutes	165°C
10 minutes	180°C
8 minutes	200°C

Application properties of the starting formulation

Substrates: Q-panel, Type ALQ-36, chromated aluminium 0,8 mm
 Film thickness: approx. 80 µm

Gloss 60°	> 90
Reverse impact, ASTM D 2794, bell diameter 5/8"	full
Buchholz hardness, DIN 53153	> 91
Pencil hardness, Wolff-Wilborn Type 291	H
Cross cut adhesion, DIN 53151, 1 mm	Gt-0
Humidity test DIN 50017-KK	≥1500 hrs
Salt Spray test DIN 50021 - SS/ASTM B117	≥ 1500 hrs
Kesternich test DIN 55018 KFW 0.2 S	≥ 30 cycles

Information is provided in good faith, no liability can be accepted.