Grilonit® RV 1802

p-tert. Butyl phenyl glycidyl ether



Characteristics

- good acid and water resistance
- maximum mechanical values
- limited diluting effect
- aromatic
- can be used to replace Grilonit® RV 1805 (ortho-cresyl glycidyl ether)

Product Specifications

Epoxy value	[eq/100g]	0.435 – 0.460	
Colour Gardner			0 - 3
Hydrolysable chlorine	[%]	max.	0.2
Water	[%]	max.	0.2

Typical Properties

Density at 20°C	[g/cm^3]	1.03
Viscosity (Höppler) at 25°C	[mPa*s]	20
Flash point, (Abel-Pensky)	[°C]	135
Vapour pressure at 20°C	[mbar]	2.3

EMS-GRILTECH has the capability to produce many other glycidyl ethers and esters. Make use of our expertise.

Recommendations are given in good faith, but are not guaranteed. No liability can be accepted. This also applies to third-party patent rights.

30.11.2009

EMS-CHEMIE AG
Business Unit EMS-GRILTECH
Via Innovativa 1
CH-7013 Domat/Ems
Phone +41 81 632 7202, Fax +41 81 632 7407
www.emsgriltech.com